

Full coated top and single coated reverse side solid bleached board (SBB).


Features

- Silky top surface
- Superior brightness level and high board gloss
- Excellent bulk and stiffness
- Outstanding printing and finishing properties
- High UV light fastness
- Resistance to ageing

Full coated top side

Base board (100% virgin fibre)

Single coated reverse side



PROPERTY	UNITS	METHODS	TYPICAL VALUES					
BASIS WEIGHTS	g/m ²	ISO 536	235.0	255.0	285.0	315.0	345.0	365.0
THICKNESS	µm	ISO 534	257.0	283.0	325.0	367.0	407.0	437.0
BENDING FORCE (15°/50 MM) MD	mN	ISO 5628 2493	110.0	160.0	230.0	320.0	430.0	490.0
BENDING FORCE (15°/50 MM) CD	mN	ISO 5628 2493	55.0	80.0	120.0	165.0	215.0	240.0
BENDING MOMENT (15°) MD	mNm	TABER T489-OM-92	5.3	7.7	11.1	15.5	20.8	23.7
BENDING MOMENT (15°) CD	mNm	TABER T489-OM-92	2.6	3.9	5.8	8.0	10.4	11.6
BENDING STIFFNESS (5°/50 MM) MD	mNm	DIN 53121	9.7	15.0	23.0	33.0	40.0	47.0
BENDING STIFFNESS (5°/50 MM) CD	mNm	DIN 53121	4.7	8.5	14.0	17.0	22.0	27.0
BRIGHTNESS (R457) SMOOTH, FULL COATED SIDE	%	ISO 2470-2	101.5	101.5	101.5	101.5	101.5	101.5
WHITENESS (CIE) SMOOTH, FULL COATED SIDE	%	ISO 11475	132.0	132.0	132.0	132.0	132.0	132.0
L-VALUE SMOOTH, FULL COATED SIDE	%	ISO 5631	95.5	95.5	95.5	95.5	95.5	95.5
A-VALUE SMOOTH, FULL COATED SIDE	-	ISO 5631	2.00	2.00	2.00	2.00	2.00	2.00
B-VALUE SMOOTH, FULL COATED SIDE	-	ISO 5631	-9.00	-9.00	-9.00	-9.00	-9.00	-9.00
BRIGHTNESS (R457) ROUGH, SINGLE COATED SIDE	%	ISO 2470-2	100.0	100.0	100.0	100.0	100.0	100.0
B-VALUE ROUGH, SINGLE COATED SIDE	-	ISO 5631	-9.00	-9.00	-9.00	-9.00	-9.00	-9.00
SURFACE ROUGHNESS SMOOTH, FULL COATED SIDE	µm	ISO 8791-4	1.8	1.8	1.8	1.8	1.8	1.8
MOISTURE CONTENT ABS.	%	DIN EN ISO 287	5.5	5.5	5.5	5.5	5.5	5.5

Test climate 23°C, 50 % relative humidity, DIN EN 20 187
All rights to improve quality due to technical modifications reserved

Printing processes

- Offset
- Screen printing
- Flexo

Available in

- Sheets
- Reels

Conversion process

- Lacquering - UV, water based and conventional, foil and film lamination, hot foil stamping and cold foil transfer, embossing (high, relief, structure, micro), die cutting, creasing, grooving, perforating, flock coating, lasercodable.

Compliance

- Suitable for direct food contact in accordance with recommendation BfR XXXVI, FDA and Austrian food legislation
- Taint and odour neutral
- Meets the purity requirements of toy safety (heavy metal content)
- Available on request as FSC Mix Credit (FSC™-C015022) or 100% PEFC (PEFC/07-32-76) certified

End uses

- High quality graphic and packaging applications

For more information please visit www.sappi.com

This document is for information purposes only. The information given has been prepared to the best of our knowledge i.e., based on due diligence and the state of research at the time of its release date. It does not provide any warranty or guarantee for specific properties or for suitability for a specific purpose or application. The responsibility for testing the suitability of the product for specific applications lies entirely with the purchaser. We reserve our right to change this document at any time.